

CERAMIC REPAIR PUTTY

DESCRIPTION

A high performance, trowelable, ceramic-filled epoxy for rebuilding worn or damaged equipment.



INTENDED USE

Industrial use: To rebuild worn pump casings and suction plates; repair tube sheets, heat exchangers and other circulating water equipment; restore worn chutes and hoppers; repair and rebuild butterfly and gate valves.

PRODUCT FEATURES

Excellent chemical resistance, Corrosion-, cavitation-, erosion-resistant, Non-sagging putty, creamy paste

LIMITATIONS

Suitability of product is determined by the end user for their application and process.

TYPICAL PHYSICAL PROPERTIES

Technical data should be considered representative or typical only and should not be used for specification purposes

Cured 7 Days @ 75°F (24°C)	Typical Values	Standard Tests
Adhesive Tensile Shear (GBS)	2,000 psi (13.8 MPa)	Coeff. of Thermal Exp. ASTM D 696
Coefficient of Thermal Expansion (x10-6)	23.8 in/in.°F (42.8 cm/cm.°C)	Compressive Strength ASTM D 695
Compressive Strength	12,700 psi (87.5 MPa)	Cured Shrinkage ASTM D 2566
Cured Shrinkage	0.0022 in/in (cm/cm)	Dielectric constant ASTM D 150
Dielectric Constant	4.1 @ 1 MHz	Dielectric strength ASTM D149
Dielectric Strength	370 volts/mil (14.6 kV/mm)	Flexural Strength ASTM D 790
Flexural Strength	6,475 psi (44.7 MPa)	Hardness Shore D ASTM D 2240
Hardness	86 Shore D	Thermal Conductivity ASTM C 177
Solids by Volume	100%	Tensile Shear ASTM D1002
Temp. Resistance	Wet 150°F (65°C); Dry 350°F (177°C)	
Thermal Conductivity (x10-3)	1.88 cal/(sec.°C.cm)	

Uncured Properties @ 72°F (23°C)	Typical Values
Color	Dark Blue
Coverage (1/4" / 6.35mm)	66 in2/lb (939 cm2/kg)
Functional Cure	16 hrs.
Max.Thickness without Sag	1/2" (12.7 mm)
Mix Ratio by Volume	4.3:1

Mix Ratio by Weight	7:1
Mixed Viscosity	Putty
Pot life@75F (24C)	25 min.
Recoat Time	2 – 4 hours
Recommended Thickness	1/4" (6.35 mm)
Specific Gravity	14.1 lb/gal (1.69 g/cm3)
Specific Volume	16.4 in3/lb (0.59 cm3/g)

SURFACE PREPARATION

1. Thoroughly clean the surface with a solvent such as Isopropanol Alcohol or Acetone to remove all oil, grease and dirt.
2. Grit blast surface area with 8-40 mesh grit, or grind with a coarse wheel or abrasive disc pad, to create increased surface area for better adhesion (Caution: An abrasive disc pad can only be used provided white metal is revealed). Desired profile is 3-5mil, including defined edges (do not "feather-edge" epoxy).

Note: For metals exposed to sea water or other salt solution, grit-blast and high-pressure-water-blast the area, then leave overnight to allow any salts in the metal to "sweat" to the surface. Repeat blasting to "sweat out" all soluble salts. Perform chloride contamination test to determine soluble salt content (should be no more than 40 ppm).

3. Clean surface again with a solvent such as Isopropanol Alcohol or Acetone to remove all traces of oil, grease, dust or other foreign substances from the grit blasting.
4. Repair surface as soon as possible to eliminate any changes or surface contaminants.

WORKING CONDITIONS: Ideal application temperature is 55 to 90°F (13-32°C). In cold working conditions, directly heat repair area to 100-110°F (38-43°C) prior to applying epoxy and maintain at this temperature during product cure to dry off any moisture, contamination or solvents, as well as to achieve maximum performance properties.

Homogenous mixing of resin and hardener is essential for the curing and development of stated strengths.

MIXING INSTRUCTIONS

It is strongly recommended that full units be mixed, as ratios are pre-measured.

1. Add hardener to resin.
2. Mix thoroughly with screwdriver or similar tool (continuously scrape material away from sides and bottom of the container) until a uniform, streak-free consistency is obtained.

INTERMEDIATE SIZES: (1, 2 & 3 lb / 0.5, 0.9, & 1.4 Kg) containers. Place resin and hardener on a flat, disposable surface such as cardboard, plywood or plastic sheet. Use a trowel or wide-blade tool to mix the material as in Step 2 above.

LARGE SIZES: (25, 30 & 50 lb / 11.4, 13.6, & 22.7 Kg) buckets: Use a T-shaped mixing paddle or a propeller-type Jiffy Mixer Model ES on an electric drill. Thoroughly fold putty by vigorously moving paddle/propeller up and down until a homogenous mix of resin and hardener is attained.

APPLICATION INSTRUCTIONS

Spread mixed material on repair area at a minimum thickness of 1/4" (6.35 mm). Work firmly into substrate to ensure maximum surface contact. Ceramic Repair Compound functionally cures in 16 hours, at which time it can be machined, drilled, or painted.

FOR BRIDGING LARGE GAPS OR HOLES

Place fiberglass sheet, expanded metal, or mechanical fasteners between repair area and Ceramic Repair Compound prior to application.

FOR VERTICAL SURFACE APPLICATIONS

Ceramic Repair Compound can be troweled up to 1/2" (13 mm) thick without sagging.

FOR MAXIMUM PHYSICAL PROPERTIES

Cure at room temperature for 2.5 hours, then heat cure for 4 hours @ 200°F (93°C).

FOR ± 70°F (21°C) APPLICATIONS

Applying epoxy at temperatures below 70°F (21°C) lengthens functional cure and pot lifetimes. Conversely, applying above 21°C shortens functional cure and pot life.

Can withstand processing forces.

Do not drop, shock load, or heavily load.

STORAGE

Shelf life 3 yrs from manufacture. See package label. Store at room temperature, 70°F (21°C)

COMPLIANCES

None.

CHEMICAL RESISTANCE

Chemical resistance is calculated with a 7 day, room temp. cure (30 days immersion) @ 75°F (24°C)

1,1,1-Trichloroethane	Excellent
Aluminum Sulfate 10%	Excellent
Benzene	Excellent
Chlorinated Solvent	Excellent
Gasoline (unleaded)	Excellent
Hydrochloric 10%	Excellent
Kerosene	Excellent
Mineral Spirits	Excellent

Nitric Acid 10%	Poor
Phosphoric 10%	Very good
Potassium Hydroxide 40%	Excellent
Sodium Hydroxide 50%	Excellent
Sodium Hypochlorite	Excellent
Sulfuric 10%	Very good
Sulfuric 50%	Fair
Toluene	Excellent

PRECAUTIONS

FOR INDUSTRIAL USE ONLY: Please refer to the appropriate Safety Data Sheet prior to using this product.

WARRANTY

ITW Polymers & Fluids will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.

ORDER INFORMATION

Item No.	Package Size
D11705	500gm
D11700	1.5kg

CONTACTS

ITW Polymers & Fluids
100 Hassall St Wetherill Park
NSW 2164 Australia
AU Phone: 1800 000 945
itwpf.com.au

ITW Polymers & Fluids
Unit 2 / 38 Trugood Drive
East Tamaki, 2013, Auckland, New Zealand
NZ Phone: 0800 476 265
itwpf.co.nz

EMERGENCY:
AU: 1800 033 111
NZ: 0800 734 607

DISCLAIMER

All information on this data sheet is based on laboratory testing and is not intended for design purposes.
ITW Polymers & Fluids and Devcon® makes no representations or warranties of any kind concerning this data.